

### TerraTuf™ – PAVERS > HEXAGON

#### ABOUT

A wide range of rubber flooring, in pavers, in an extensive collection of colors and for walkways and equine floorings.

Made of Styrene-Butadiene Rubber (SBR) which is a copolymer of styrene and butadiene characterized for durability and abrasion resistance



#### PERFORMANCE ATTRIBUTES

- Compatible with most floor finishes.
- Easy to carry and install.
- Natural elasticity reduces noise.
- Anti-fatigue
- Crack isolation membrane protects ceramic tile, porcelain and stone tile

#### DIMENSIONS

- Size: 23 x 23 cm
- Thickness (mm): 25, 30, 40, 45, 50
- Standard Tolerances : Width: +/- 2mm  
Length: +/- 2mm  
Thickness: +/-2mm

#### MATERIAL

- 100% SBR granulate in 7 color variations
- 85% SBR granulated + 15% EPDM granulated in 20+ color combination

#### TECHNICAL DATA

PROPERTY	TEST METHOD	UNITS	TEST RESULTS
Dimensional Stability	AS 2498.6	+/-1mm (23 to 70°C)	<1.0mm
Duro – Shore Hardness	AS 1683.15.2	Shore A	60-70
Density	ISO 845 Method A	Kg/m <sup>3</sup>	950-1020
Color Fastness (UV resistance)	SAE J2020 QUV accelerated Weathering	No chalkiness or color change after 500hrs	No color change after 500hrs
Shear Strength	ISO 1827	Mpa	2.56
Compression Strength @ 20%	ASTMD 575	Mpa	1.20
Compression Young's Modulus	ASTMD 575	Mpa	0.26
Tensile Strength	ISO 39-2005	Mpa	3.03
Elongation at tear	AS 1683.12	%	50
Heat Conductivity	ASTM C518	W/mK	0.1906
Heat Resistance/thermal, resistance, K factor conditions (Nominal temp 25°C)	ASTM C518 THICKNESS 24-45mm	m <sup>2</sup> K/W	0.1283

\*The values & properties stated above are carried out in our lab for the component used in the production. However, they do not constitute a guarantee for a specific product feature & do not establish a legal contract

#### CERTIFICATIONS



#### CONTACT

+971 4 263 2332 | +971 55 325 2253  
 inquiry@terrainfloorings.com  
 terrainfloorings.com

